

TrendStone® **Retaining Wall System**

PRODUCT DATA SHEET

Date: December 2019	Product Name: See Below				
Product Code: See Below	This data represents average results from commercial production lots. If specific test results				
Description: Retaining Wall Blocks	are required, samples should be taken from current production lots.				
	Apex Masonry - TrendStone® Retaining Wall System is manufactured in accordance with the provision of				
Manufactured: Maryborough, QLD	Australian Standards AS/NZS4455.1997 - for masonry units.				
Application: Retaining Walls, Straight & Curved Walls, Planter Boxes, Garden Walls &	Content: Cement, Sand, Aggregate, Colour Oxide & Sealer.				
Edges, Steps & Courtyards	For walls over 1m refer to engineering specifications.				



SPECIFICATIONS											
Product Code	Product Name	Dimensions			Weight	Block Per	No Per	Durability Class	F'uc		
		Length (mm)	Width (mm)	Height (mm)	(kg)	m²	Pallet	Durability Class	(MPa)		
60-TSWALL_	TrendStone Wall Unit	400	245	200	21.06 - 22.45	12.5	78	General Purpose	>15		
60-TSCAP_	TrendStone Capping Unit	400	255	65	14.08 - 14.49	2.5	120	General Purpose	>15		
60-TSCNR_	TrendStone Corner Unit	390	190	200	20.00 - 21.28		75	General Purpose	>15		

CAUTION: Silica dust may be released when working with quarry products or when concrete masonry are cut, drilled, sawed, routed, chased, sanded, broken up or ground. Where contact occurs to eyes or skin wash thoroughly immediately and if inhaled move straight to fresh air, repeated long term exposure to silica dust may lead to lung diseases. To prevent this, use suitable extractive equipment, protective clothing and gear.